

URS 2482

DYNAMIC PERFORMANCE POLYURETHANE CASTING SYSTEM

82 SHORE A

DESCRIPTION

URS 2482 is a polyether based urethane casting system with excellent dynamic and mechanical properties. **URS 2482** is recommended for highly abrasive or high flex applications such as slurry pumps, sizing screens, rollers, wheels, shock pads, etc.

FEATURES

Excellent Flex Life
Outstanding Abrasion Resistance
Superior Resistance To Water
No MOCA or TDI
Hand or Machine Processing
Excellent Low Temperature Properties – 40 Deg F

LIQUID

<u>PROPERTIES</u>	<u>POL 580B</u>	<u>ISO 110A</u>	<u>MIXED</u>
Appearance	Amber Liquid	Amber Liquid	Amber Liquid
Viscosity (cps)	1,000 – 2,000 (100 F)	500 – 1,000 (77 F)	800 – 1,200 (100 F)
Density (lbs/gal)	8.10 – 8.25	10.0 -10.2	8.75 – 8.95

PHYSICAL PROPERTIES

Hardness, Shore A	82-A
Modulus, psi 100%	820
200%	1410
300%	1900
Tensile Strength, Ultimate, psi	5400
Elongation, %, 460	
Tear Strength, "Die C" lbs/in	520
Compression Set, Method B	25

URS 2482 Cont:

PROCESSING PARAMETERS

Melt and process polyol 580B at 100 to 150 degrees F.

Melt Isocyanate 110A if frozen at 100 degrees F., otherwise use at 70 to 85 degrees F.

Mold Temperature: 100 to 180 degrees F.

Mix ratio: 100.00 parts Polyol 580B to 60 parts Isocyanate 110A by weight.

Degas mixture if possible or pre-degas Polyol in dispensing equipment prior to casting.

Pot life: (200g mass) (100 degrees F) 8 to 12 minutes.

Demold: 1 - 2 hours or 30 – 45 minutes with maximum process and mold temperature .
Catalyst may also be used to shorten demold time.

Post Cure: 16-24 hours @ 140 degrees F.

STORAGE

Systems should be stored unopened in air tight containers at 60-90 degrees F. Partially emptied containers should be swept free of atmospheric moisture with dry nitrogen before sealing.

HANDLING PRECAUTIONS

For complete and updated health and safety information, read the MATERIAL SAFETY DATA SHEETS. Do not handle or use until the MATERIAL SAFETY DATA SHEET has been read and understood.