

URS 2486

DYNAMIC PERFORMANCE POLYURETHANE CASTING SYSTEM

86 SHORE A

DESCRIPTION

URS 2486 is a polyether based urethane casting system with excellent dynamic and mechanical properties. URS 2486 is recommended for highly abrasive or high flex applications such as slurry pumps, sizing screens, rollers, wheels, shock pads, etc.

FEATURES

Excellent Flex Life
Outstanding Abrasion Resistance
Superior Resistance To Water
No MOCA or TDI
Hand or Machine Processing
Excellent Low Temperature Properties-40 Deg F

<u>Liquid Properties</u>	<u>POL 160B</u>	<u>ISO 110A</u>	<u>Mixed</u>
Appearance	Amber Liquid	Amber Liquid	Amber Liquid
Viscosity (cps)	1,000-2,000(100F)	500-1,000(77F)	800-1,200(100F)
Density (lbs/gal)	8.10-8.25	10.0-10.2	8.85-9.00

PHYSICAL PROPERTIES

Hardness, Shore A	86
Modulus, psi, 100%	910
200%	1670
300%	2350
Tensile Strength, Ultimate, psi	5100
Elongation, %	390
Tear Strength "Die C" lbs/in	515
Compression Set, Method B	27
Bayshore Rebound, %	46

URS 2486 cont:

PROCESSING PARAMETERS

Melt and process polyol 160B at 100 to 150 degrees F.

Melt Isocyanate 110A if frozen at 100 degrees F., otherwise use at 70 to 85 degrees F.

Mold Temperature: 100 to 180 degrees F.

Mix Ratio: 100 parts polyol 160B to 65 parts Isocyanate 110A by weight.

Degas mixture if possible or Pre-degas polyol in dispensing equipment prior to casting.

Pot Life: (200g mass) (100 F) 8 to 12 minutes.

Demold: 1-2 hours or 30-45 minutes with maximum process and mold temperature. Catalyst may also be used to shorten demold time.

Post Cure: 16-24 hours @ 140 degrees F.

STORAGE

Systems should be stored unopened in air tight containers at 60-90 degrees F. Partially emptied containers should be swept free of atmospheric moisture with dry nitrogen before sealing.

HANDLING PRECAUTIONS

For complete and updated health and safety information, read the MATERIAL SAFETY DATA SHEETS. Do not handle or use until the MATERIAL SAFETY DATA SHEET has been read and understood.